

CEMCURE WB

Water Based Concrete Curing Compound

Description:

CEMCURE WB is a sodium silicate water-based resin modified concrete curing compound. It is formulated that when applied to freshly casted concrete it prevents rapid evaporation of water from the concrete surfaces.

CEMCURE WB acts as a barrier retaining the mix water in the concrete to ensure proper reaction and cement hydration. The result is a high surface strength, high resistance to abrasion and protection from drying shrinkage. CEMCURE WB is an environmentally friendly product.

Uses:

CEMCURE WB is used as an effective and economical curing agent compared to the traditional Hessian, water and polythene curing system. It is suitable for all types of concrete surfaces, including the following applications:

- Curing of shear walls, slabs and columns newly casted.
- Can be applied for curing large areas effectively, such as pre-cast concrete, highways, decks, etc.
- Curing of casted cement pipes
- Can be used as dustproof, clear sealer for concrete surfaces.

Advantages:

- Uniform hydration which gives durable concrete.
- Cost effective, with high curing efficiency.
- Non filming effect. Plaster can be applied directly.
- Reduces surface cracking and shrinkage.
- Resistance to oil and grease.
- Serves as dust proofer/sealer for concrete casted floors.
- Ease of application, applied manually or by spray pump.
- Water based, environmentally friendly product.

Instructions for Use:

Mixing:

CEMCURE WB should be well stirred before each application. Do not apply CEMCURE WB if temperature is less than 5°C. Do not dilute with water as the product is ready to use.

Application:

CEMCURE WB should be applied uniformly by paint roller, soft bristled broom, or spraying machine to the surface of fresh concrete. The timing of application is important. CEMCURE WB should be applied after setting of cement, immediately after evaporation of the surface water. The surface should be free of bleed water and the concrete surface sheen should not be seen. It is during this time that the concrete is most vulnerable to spalling, hair cracking, and other surface defects. In the case of vertical concrete elements, CEMCURE WB should be applied immediately on removal of the formwork.

Apply CEMCURE WB with a rate of 1 liter per 10m² of concrete surface. In certain cases, especially during high temperature or windy seasons, prevent the surface from drying to ensure thorough penetration. After the application of CEMCURE WB, allow the curing compound to dry properly, do not apply any water to the coated surface.

CEMCURE WB should never be applied on concrete which has started to dry out, otherwise the hydration mechanism will be seriously impaired.

Subsequent application as cement plaster, key coat, bituminous, acrylic coatings, or tile fixing using latex modified tile adhesive, can be done after removal of residual remains of CEMCURE WB. It is, recommended to check the adhesion of any particular application by carrying out a site trial test to ensure a satisfactory performance. If the product is applied at a high rate, a film will be created on top of the concrete surface. In such case, the film should be removed.

CEMCURE WB

Standard:

CEMCURE WB meets the moisture requirement of ASTM C309 on concrete.

Coverage:

CEMCURE WB coverage rate is approx. 10 square meters per liter at 100-micron wet film thickness.

*Coverage rate is an approximate value, and subject to actual site conditions.

TECHNICAL PROPERTIES	
Color	Clear
Density	1.15 ± 0.03 kg/lit
Curing Efficiency (ASTM 7542)	>75%
Max. time for application	30 minutes@25°C
pH	10-12
Temperature of Application	+5°C min, +40°C max
Drying time	<1 hour at 25°C Depending on-site condition

*Values indicated may vary depending on the environment and conditions of the material. Figures given are tested according to standard laboratory conditions.

Packaging:

CEMCURE WB is supplied in 200 liter drums.

Storage Conditions:

Store in original packing in dry conditions away from direct sunlight. Damaged packaging, high humidity or extreme temperatures may reduce the shelf life. Store between 10°C to 30°C.

Shelf Life:

CEMCURE WB can be utilized within 12 months of production date if stored in proper conditions in an unopened original packing.

Cleaning:

Used tools can be cleaned with water before the product dries.

Recommendations:

- Weather factors such as wind, heat greatly reduce the effectiveness of CEMCURE WB.
- Use only on green, fresh poured concrete.
- Protect areas not intended for coverage. If contact occurs, clean immediately using water and a cloth or brush.
- Do not allow the product to puddle. White residue may form if CEMCURE WB is over applied.
- Do not apply when ambient temperature is < 5°C.
- In spite that CEMCURE WB is compatible with and provides good adhesion to most emulsion paints, asphalt and polymer modified cements, it is imperative that site testing be performed to determine the suitability for intended use.
- Do not use sprayers, which have been used to spray silicones or release agents.
- Ensure spraying equipment is cleaned thoroughly before use and residues of previous membranes are removed.
- CEMCURE WB must not be applied before or during power floating operations.

Health and Safety:

Avoid contact with eyes and skin. Wear suitable protective clothing such as coveralls, goggles, dust mask and gloves. Use barrier cream. Ensure that there is adequate ventilation. Do not breathe vapor or spray mist.

FIRST AID:

- | | |
|-------------|---|
| Eyes: | In the event of accidental splashes, flush with warm water and seek medical advice. |
| Skin: | Wash skin thoroughly with soap and water |
| Inhalation: | Remove to fresh air, keep patient rested |
| Ingestion: | Do not induce vomiting. Seek immediate medical attention. |

For further safety information, please refer to CEMCURE WB Material Safety Data Sheet.

MATEX Rev.13-0425

MATEX warrants that its products are free from material and manufacturing defects. Instructions on how to use the product should be strictly followed to ensure effectivity and safe use. MATEX shall not be liable either directly or indirectly for any damages to personal, equipment or products that may occur as a consequence of the failure of any products application because it has no direct or continuous control over where or how its products are applied. It is the user's responsibility to acquire always the updated version of datasheets.

