

HYDROBIT SBW

Elastomeric SBS Modified Water Based Waterproofing Membrane

Description:

HYDROBIT SBW is a high build water based elastomeric liquid applied waterproofing membrane based on modified bitumen, Styrene butadiene styrene 'SBS' copolymers and carrier water. HYDROBIT SBW has excellent adhesion to most substrates including concrete, plaster, masonry, bituminous roofing felts, and metal and asphalt coatings. HYDROBIT SBW cures to form a seamless, high flexible, continuous monolithic membrane that has excellent adhesion to most substrates including concrete, cement blocks, wood and existing roofing felts. It is ideally recommended as a superior waterproofing application for building structures including foundations, kitchen and toilet floors, building facades and roofs.

Applications:

- Damp proofing of facades.
- Wet areas, kitchens and bathrooms waterproofing.
- Damp proofing of cement sheets.
- Waterproofing concrete panels with potential of movement.
- Foundation waterproofing.
- Roofing and corrugated sheets waterproofing.
- Cement pipes and metal.
- Waterproofing of cold store walls.

Advantages:

- Water based, friendly product with no odour risk.
- Superior water proofing membrane.
- Elastomeric, highly flexibility up to 1000%.
- Vapor permeable allows substrate to breathe.
- Excellent resistant to chloride and sulphate attacks
- Excellent adhesion to substrate
- Ideal maintenance solution for waterproofing damages roofing membrane
- Easy application due to paintable consistency.
- Ensure great protection against corrosion.
- Resistant to underground soil ground water aggressive effect.

Instructions for Use:

Surface Preparation:

Concrete substrate should be fully cured, dry, free from dust, oil, curing agent residues and other contaminants. All shrinkages and non-moving structural cracks under 1.0 mm shall be covered with 1.0 mm thick strip of HYDROBIT SBW extended to 50 mm on both sides of the crack. For parapet walls, columns, pipes penetrations etc. make a 45° coving fillet at all corners using LAVAREP F40. Apply a reinforcing strip of HYDROBIT SBW 1 mm thick extending 150 mm on both sides of the coving to form an over flashing. Voids and honeycombs must be patched with MATEX concrete repair products. Allow the patched area to cure before applying the membrane.

All metal surfaces should be made clean of paint, oils, rust and other contaminants. Apply sand blasting or mechanical preparation to expose bright metal then wipe clean the surface prior to priming.

Normally good quality concrete substrates does not require priming. In case of porous surfaces application of primer is recommended to eliminate the blisters caused by air entrapments. Use HYDROBIT SBW thinned with 20% water as a primer. To join fresh applications of HYDROBIT SBW to those that are more than 48 hours old, apply diluted HYDROBIT SBW with 10% water as a primer at the interface.

Mixing:

HYDROBIT SBW is a single component ready to use emulsion. Shake the barrel well to mix any settled material only.

HYDROBIT SBW

Application:

HYDROBIT SBW can be applied with a roller, trowel, brush or spray machine. It is recommended to apply two coats to achieve a dry film thickness of 1.5 mm. in case of roller or brush applications, apply the first coat to the surface in a spread rate of 1.0 kg/m² per. second coat should be applied to the first coat after it cures with same rate of application preferably in 90 degree direction.

For enhanced protection of concrete surfaces, or when the substrate is affected by mechanical loads, it is recommended that all weak areas including surface cracks, joints and areas around pipes and projections, be reinforced by embedding woven fiberglass mesh strips between two coats of HYDROBIT SBW.

Do not leave the applied product exposed for elongated periods, as mechanical damages might occur to the monolithic membrane. Once the membrane cures, apply protection sheets or screed mortar to ensure proper protection.

HYDROBIT SBW can be applied on several kind of surfaces such as concrete, blocks, brick, corrugated sheets, asbestos. For application on metal surface (zinc, steel, etc.), it is not recommended to keep it exposed as the coating will be soften and crack due to high temperature climate.

Tile adhesives can be applied to HYDROBIT SBW membrane after it is completely cured. To provide a good mechanical key with the membrane, spread the final coat of HYDROBIT SBW with clean silica sand while it is still wet. Finished flooring installations should be carried out as soon as possible after full cure of membrane is established.

HYDROBIT SBW may be applied to damp but not wet surfaces, dampen brushes before and occasionally during use to avoid clogging and ease application. During hot, dry weather application may be assisted by dampening the surfaces to be treated.

Standards:

HYDROBIT SBW conforms to:
BS 6949, ASTM C 309 – 96, ASTM D2939

Shelf Life:

HYDROBIT SBW can be utilized within 12 months of production date if stored in proper conditions in unopened original packing.

Packaging:

HYDROBIT SBW is available in 20 liter pails and 200 liter metallic drum.

Coverage:

HYDROBIT SBW achieves coverage of 1.15 kg per square meter per coat for 1 mm thickness.

Storage:

Store in original packing in dry conditions away from direct sunlight.

TECHNICAL PROPERTIES

Solid Contents	: 70%
Elongation	: >1000%
Specific Gravity	: 1.1 @ 25°C
Service Temp.	: -10°C to + 85°C
Recovery	: >100%
Flashpoint	: N/A
Drying Time	: 4 hours at 35°C
Over Coating Time	: 14 hours at 35°C
Rubber content	: 20%
Appearance	: Dark black/brown coating. Cures to a hard tack free finish.
Resistance to water (ASTM D 2939)	: Pass
Tensile Strength	: >15 N/cm ²
Vapor Permeability	: 0.25g/m ² /24h

Cleaning:

Clean all tools with clean water before product hardens.

HYDROBIT SBW

Health and Safety:

Avoid contact with eyes and skin. Wear suitable protective clothing such as coveralls, goggles, dust mask and gloves. Use barrier cream. Ensure that there is adequate ventilation. Do not breathe vapor or spray mist.

FIRST AID:

- | | |
|-------------|---|
| Eyes: | In the event of accidental splashes, flush with warm water and seek medical advice. |
| Skin: | Wash skin thoroughly with soap and water |
| Inhalation: | Remove to fresh air, keep patient rested |
| Ingestion: | Do not induce vomiting. Seek immediate medical attention. |

For further safety information, please refer to HYDROBIT SBW Material Safety Data Sheet.

MATEX Rev.07-0823

MATEX warrants that its products are free from material and manufacturing defects. Instructions on how to use the product should be strictly followed to ensure effectivity and safe use. MATEX shall not be liable either directly or indirectly for any damages to personal, equipment or products that may occur as a consequence of the failure of any products application because it has no direct or continuous control over where or how its products are applied. It is the user's responsibility to acquire always the updated version of datasheets.

