

TILEGRIP MT

Mosaic and Glass, Tile Adhesive & Grout

Description:

TILEGRIP MT is a high performance, mold resistance, waterproof, bright white cementitious adhesive and grout with vertical slip resistance designed to installing sheet-mounted glass and marble mosaic. It is a particular fine white powder composed of cement, graded aggregates, high organic polymer content and special additives.

TILEGRIP MT is a formulated with high flexibility and waterproofing characteristics to withstand the movement and vibration of mosaic tiles and to act as a water and frost resistant tile adhesive. It bonds to dry areas of most types substrates including rendered surfaces, plaster board, old glazed tiles, AAC block and emulsion paint walls.

Uses:

TILEGRIP MT is suitable for use in kitchens, bathrooms and outdoor areas subject to frequent and prolonged water exposure and for domestic shower walls and glass tile backsplash installations when applied using a solid adhesive bed. It is used as adhesive, as well as, joint grout in the same application for installing mosaic and glass tiles for interior and exterior floor and wall tiles.

TILEGRIP MT mixed with ELASTOGRIP can be used for:

- Installing glass mosaic or ceramic tile on non-absorbent surfaces.
- Installing glass mosaic or ceramic tiles in swimming pools, basins or similar structures even on absorbent substrates.
- Submerged installations (pools, fountain, water features)

Advantages:

TILEGRIP MT when mixed with water, becomes a mortar with the following features:

- Excellent adhesive to most conventional materials used in building.

- Highly thixotropic. Mosaic tiles can be installed from the top towards the bottom without using spacer pegs.
- Particularly extended open and adjustability time, making installation easier.
- Non sag performance: Great for sheet-mounted mosaics where final alignment is critical
- Bright white color enhances the appearance of transparent or translucent glass or stone tile.
- Can be mixed with ELASTOGRIP (instead of water) for increased performance and installation of tiles in submerged applications.

Instructions for Use:

Surface Preparation:

All substrates should be structurally sound, stable, dry, clean, and free of any substance or condition that may reduce or prevent proper adhesion. Before Applying TILEGRIP MT, moisten the cementitious substrate with clean water to reduce the possible absorption of water from the mix.

Mixing:

Place 4.2–4.50 liters of cold, potable water (or ELASTOGRIP as needed) into a clean mixing bucket. Add slowly 20 kg bag of TILEGRIP MT under continuous mixing till a uniform lump free consistency mix is achieved. For mixing process, a slow speed drill (200- 300rpm) fitted with a suitable paddle is recommended. Allow the obtained mix to stand for 5 minutes and then remix before application. If mixture becomes heavy within one hour remix without adding more water.

Application:

Consult the glass tile manufacturer's specification to verify product suitability for specific installations and installation procedures.

Choose a typical notched trowel with sufficient depth to achieve mortar contact to both the tile and substrate. Glass mosaic installations require 100% continuous coverage between tiles and substrate (ANSI A108.5 specifications).

TILEGRIP MT

Spread TILEGRIP MT on the substrate to a uniform thickness of 3 mm using the flat side of the spatula, the first pass with its smooth part and the second pass, immediately after, to the desired thickness using the toothed part.

Place the tiles firmly onto the adhesive bed. Apply sufficient pressure on the tile during fixing with slight twisting movement in order to ensure good contact with the mortar.

Apply only as much mortar that can be tiled during the adhesive's open wet time. Spreading large areas may result in drying the adhesive before tiles can be fixed causing poor adhesion. Open time can vary depending on weather and site condition.

For the installation of sheet-mounted glass and marble mosaics, after using light pressure to establish contact with the fresh mortar, light pressure to establish contact with the fresh mortar, lightly tap the tile with a rubber-hammer. Remove all mortar from mosaic tile surfaces. Always start installing the mosaic sheet from top towards the bottom.

Standards:

- European EN 12004 C2T
- ANSI A 118.4 – 1999
- ISO 13007 – C2T

If mixed with ELASTOGRIP:

- ISO 13007 – C2TS1

TECHNICAL PROPERTIES	
Color	Bright white. Other colors upon request
Dry Density	1.40 ± 0.03 kg/lit
Wet Density	1.6 ± 0.03 kg/lit
Consistency	Creamy
Open Time @ 25°C (EN 1346)	Approx. 20 mins
Workable Time	>45 minutes
Water Resistance	Excellent
Slip Resistance	Excellent
Tile Adhesion Strength (EN 1348)	
Initial (28 days)	1.6 N/mm ²
After heat ageing	1.4 N/mm ²

After water immersion	1.1 N/mm ²
After freeze-thaw cycle	1.0 N/mm ²
Shear Strength	1.65 N/mm ²
Service Temperature	-30°C to 90°C
VOC	1.0 g/l

*Values indicated may vary depending on the environment and conditions of the material. Figures given are tested according to standard laboratory conditions.

Packaging:

Available in 20 kg recyclable paper bags.

Coverage:

Solid bed	: 1.6 Kg/m ² per 1mm thickness
3mm notched trowel	: 2.4 Kg/m ² on smooth surface at 3 mm thickness
Yield	: 15.0 Ltr. for 20 Kg bag (mixed)

*Consumption will vary according to the type of tiles and support conditions.

Storage:

Store in original packing in dry conditions away from direct sunlight and high humidity levels

Shelf Life:

TILEGRIP MT can be utilized within 12 months of production date if stored in proper conditions in an unopened original packing.

Cleaning:

Clean tools with water prior to product hardening. Hardened materials can only be removed mechanically.

Recommendations:

- It is always recommended to submit tile sample to MATEX technical department to confirm the compatibility of adhesive with tile.
- Floor and wall coverings installed with TILEGRIP MT must not be washed down or exposed to rain for at least 24 hours and must be protected from direct sunlight and frost for at least 5 – 7 days after the installation.

TILEGRIP MT

- Do not apply TILEGRIP MT on surface that has temperature less than 5°C or more than 35°C
- Basins and swimming pools can be filled with water after 14 days of applying TILEGRIP MT.
- While mortar is fresh, clean tools and tile with water.
- Glass tile may not be suitable over some of the substrates (such as plywood). Contact MATEX Technical Services Department for installation recommendations regarding substrates or conditions not listed.
- Do not use for moisture-sensitive stone such as green marble, red marble, black marble, some limestone, green granite, agglomerate tiles.
- To use directly over gypsum-based substrate, apply ARMOPRIME AC primer before use.

Health and Safety:

- Avoid contact with eyes and skin. Wear suitable protective clothing such as coveralls, goggles, dust mask and gloves. Use barrier cream. Ensure that there is adequate ventilation. Do not breathe vapor or spray mist.

FIRST AID:

Eyes:	In the event of accidental splashes, flush with warm water and seek medical advice.
Skin:	Wash skin thoroughly with soap and water
Inhalation:	Remove to fresh air, keep patient rested
Ingestion:	Do not induce vomiting. Seek immediate medical attention.

For further safety information, please refer to TILEGRIP MT Material Safety Data Sheet.

MATEX Rev.03-0422

MATEX warrants that its products are free from material and manufacturing defects. Instructions on how to use the product should be strictly followed to ensure effectivity and safe use. MATEX shall not be liable either directly or indirectly for any damages to personal, equipment or products that may occur as a consequence of the failure of any products application because it has no direct or continuous control over where or how its products are applied. It is the user's responsibility to acquire always the updated version of datasheets.



P.O. BOX: 29585, Dubai, UAE, Tel: +971 4 333 4140, Fax: +971 4 333 4115
Email: info@matex.ae, www.matex-global.com

